

SPORTHANE NON-EXPOSURE WATERPROOFING COAT



OVERVIEW

SPORTHANE NON-EXPOSURE WATERPROOFING COAT is a two component, polyurethane resin based waterproof coating with elongation to provide adaptability to crack of substrate.

- **Recommended Use**

As a waterproof coating for hidden area of roof and other parts of buildings.

PHYSICAL PROPERTIES

1. Finish and Color

Black, Other colors are available on request

2. Drying Time

Substrate temperature	5°C/41°F	20°C/68°F	30°C/86°F
Set to touch	10 hours	5 hours	3 hours
Dry through	48 hours	24 hours	18 hours
Fully cured	10 days	5 days	3 days

3. Spreading Rate (Theoretical)

4.85Kg/m² in 3m/m dry film thickness on a smooth surface

4. Specific Gravity

4Mixed : Approx. 1.47

5. Flash Point

27°C/80.6°F (Closed cup).

APPLICATION DETAILS

1. Surface Preparation

Do not apply coating unless concrete has cured at least 28 days at 20°C/68°F and below 80% R.H or equivalent. Moisture content of the surface must be below 6%.

The surface should be free of laitance. This can be accomplished by finishing technique, abrasive blasting, grinding, etc.

2. Preceding Coat

SPORTHANE PRIMER or according to specification.

SPORTHANE PRIMER + Scraping: SPORTHANE NON-EXPOSURE WATERPROOFING COAT (0.5~0.8mm)

3. Application Conditions

Do not apply when the temperature is less than 5°C/41°F, and relative humidity is above 80%. The surface temperatures must be at least 3°C(5°F) above dew point to prevent condensation.

4. Mixing

PTA(Part A) : PTB(Part B) = 3 : 1 (by Weight).

Mix separately, then combine together and mix thoroughly with high speed dissolver for 5 minutes prior to application.

5. Pot Life & Recoating Interval

		5°C/41°F	20°C/68°F	30°C/86°F
Pot Life		50 mins.	30 mins.	20 mins.
Recoating Interval	Min.	48 hours	24 hours	18 hours
	Max.	96 hours	48 hours	36 hours

6. Thinning

Do not dilute.

7. Method of Application

Rake, Roller, Spatula.

8. Film Thickness

Recommended per coat 2- 3m/m dry (Except for scraping)

9. Subsequent Coating

Protection mortar or according to specification.

10. Shelf Life

PTA(Part A) : 12 months

PTB(Part B) : 12 months

* Store in cool, dry, well-ventilated place.

11. Packing

PTA(Part A) : PTB(Part B) = 24 Kg : 8 Kg

Remarks

If the surface is not tacky from rain and snow, SPORTHANE PRIMER should be applied prior to application. In this time, spreading rate of SPORTHANE PRIMER is 0.1Kg/m².

Bubbling may occur in case of applying this material in the high temperature (air : above 28°C/82°F, surface : above 40°C/104°F). Do not store at temperature above 30°C/86°F. Use adequate ventilation.

Avoid contact with skin and eyes, and prolonged breathing of solvent vapors.

In case of contact, wash with organic solvent and followed by soap and water cleaning.

Respiratory protection is recommended when applying this product in confined spaces or stagnant air.

Clean equipment with SPORTHANE THINNER immediately after use.

Issued
Sep, 2012

Disclaimer : The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

